


FILM DATA SHEET

PC200



Shannon Packaging Company
14375 Telephone Ave.
Chino, CA 91710
Phone: (909) 591-8768
Fax: (909) 591-1409
www.shannonpkg.com
SPC311R1.03.18.18

Physical Description:
2mil Clear PET/Cast Poly Prop

Application:

This laminated extremely clear material is transparent and can be used for a wide variety of packaging applications where seal strength and clarity are required. This film is FDA approved and has high contact clarity. It is designed for baking and confectionary applications.

Converting:

It can be converted in many ways: 2-seal pouch, 3-seal pouch, side gusset, stand up pouch and tubing. Features include: recloseable zipper, tear notch, round hang hole, and sombrero hang hole. The PC200 can also be surface printed or reverse-trapped printed.

Physical Properties:

| PROPERTIES | TEST METHOD | UNIT OF MEASURE | TYPICAL VALUE |
|-------------|--------------|------------------------|---------------|
| Caliper | | mils | 2.0 |
| Yield | | sq.in/Lb | 54.7 |
| MVTR | Mocon | gms/100 sq. in./24 hrs | .324 |
| OTR | ASTM-1434-66 | cc/100 sq. in./24 hrs | 7.74 |
| Tensile MD | ASTM D-882 | lbs. at break | 8.858 |
| Tensile XMD | ASTM D-882 | lbs. at break | 10.932 |
| Tear MD | ASTM 689 | lbs. at break | 2.370 |
| Tear XMD | ASTM 689 | lbs. at break | 1.977 |
| Puncture | Fed. TM 2065 | Lbs. | .718 |

The values indicated in this document are the results of tests made in compliance with the normal standards. They are given as an indication and should be considered as average values and given without any obligation on our part. This data was provided directly to Shannon from our film supplier.

For more information about material data, please visit our web site at www.shannonpkg.com

*Your Solution
is in the bag*